


# SABO® STAB UV 70

Hindered amine light stabilizer (HALS) for plastics

Plastic Additives

## COMPOSITION

Chemical structure



Chemical name

Bis(2,2,6,6-tetramethyl-4-piperidyl) sebacate

CAS number

52829-07-9

## TYPICAL PROPERTIES

Appearance	White granules
Assay (GC)	>98%
Bulk density	550 kg/m <sup>3</sup>
Melting range	81-85°C
Solution transmission	>98% at 425 nm (10% in toluene)
Average particle size	0.6 mm

## FEATURES

- Excellent light stabilization performance in thick-section applications
- Non-discoloring
- Granular, low-dusting product form

## APPLICATIONS

SABO®STAB UV 70 is a low molecular hindered amine light stabilizer (HALS) which is effective in a broad range of polymers, particularly in thick-section applications. The product is particularly useful in PP, TPO, styrenic polymers (HIPS, SAN, ABS, ASA), polyamides, polyurethanes, polyacetals, acrylics, elastomers, adhesives, and sealants. It is also suitable for use in thin section applications such as PP film and tapes.

## GUIDELINES FOR USE

Typical addition levels for SABO®STAB UV 70 range from 0.05-0.6%, depending upon the application. The exact level to be used in any particular application should be determined in an appropriate testing program.

The product often shows a performance synergy with other light stabilizers, especially high molecular weight HALS (e.g. SABO®STAB UV 94, SABO®STAB UV 119), benzoates (SABO®STAB UV 37), and UV absorbers.

**SOLUBILITY DATA (g/100 g solution, 20°C)**

Acetone	47	<i>n</i> -Hexane	0.3
Chloroform	71	Methanol	0.9
Ethanol	1.5	Toluene	60
Ethyl acetate	47	Water	<0.01

**PACKAGING**

25 kg PE bag (500 kg to pallet); Pallet type : CP3

**HANDLING & STORAGE**

Please consult the Safety Data Sheet prior to handling or using this product.

If properly stored in a dry place at temperatures below 25°C, SABO®STAB UV 70 remains within the specification limits for at least 5 years.

**REGISTRATIONS**

SABO®STAB UV 70 is listed on the following national chemical inventories:

EINECS (Europe)	ENCS (Japan)	TSCA (USA)
AICS (Australia)	IECSC (China)	
DSL (Canada)	NZIoC (New Zealand)	
ECL (Korea)	PICCS (Philippines)	

This product is cleared in some countries for use in plastic materials and articles intended to come in contact with food. Please contact your Sabo representative for further information.

Additional information on SABO®STAB UV 70 is available on request from your Sabo representative, including compliance with norms and regulations in the EU, USA, and other countries.

The following supersedes Buyer's Documents. Sabo makes no representation or warranty, express or implied, including of merchantability or fitness for a particular purpose. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Sabo be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Sabo's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.